



KLINGER TOP- CHEM 2005



Modified PTFE material with excellent chemical resistance and good mechanical properties. Suitable for a wide range of applications with the exception of strong alkaline conditions

The Klinger group has been recognised as the market leader in gaskets and sealing for over a century. Our research and development laboratories have investigated over 250 different fibre forms in the search for asbestos free alternatives. The search has resulted in a range of high quality and high performance asbestos free materials that have been proven in service

GENERAL PROPERTIES

- » Economical alternative to KLINGERTop-chem-2000
- » Ideal for strongly acidic environments
- » Good mechanical properties at low to medium temperatures

TESTS AND CERTIFICATIONS

- » DIN DVGW
- » KTW-Guideline
- » FDA Conformity
- » DNV-GL
- » TA-Luft (Clean air)
- » Regulation (EU) No. 1935/2004 (incl. 10/2011)


AVAILABILITY

- » Sheetting (m): 1.5 x 1.5
- » Thickness (mm): 1.5, 2.0, 3.0

* Can be welded to form gaskets larger than sheet size

TOP-CHEM 2005

APPLICATION GUIDELINES



■ Caution: May be suitable but essential that you refer to Klinger for advice

■ Usually Satisfactory, but suggest you refer to Klinger for advice

■ Usually Satisfactory to Use Without Reference

NOTE: Chemical compatibility must be considered in all cases.

TYPICAL SPECIFICATIONS

(Typical values for 2.0mm thick material)

PROPERTIES	CONDITIONS	VALUES
Compressibility ASTM F 36 J		7%
Recovery ASTM F 36 J		35%
Stress relaxation DIN 52913	30MPa, 16h/150°C	25MPa
Klinger cold/hot compression (50MPa)	Thickness decrease at 23°	10%
	Thickness decrease at 250°C	30%
Gas leakage according to DIN 28090-2		0.02 mg/s.m
Thickness increase after fluid	H2SO4 100%:18h/23°C	2%
Immersion ASTM F 146	HNO3 100%, 18h/23°C	7%
Density		2.0g/cm ³

HEAD OFFICE

KLINGER Ltd
Wharfedale Road
Euroway Trading Estate
Bradford BD4 6SG

Tel: 01274 688 222
Fax: 01274 688 549
www.klinger.co.uk
enquiries@klingeruk.co.uk



FM 602916 FM 10571 OHS 570166 EMS 570165

KLINGER RUNCORN

Tel: 01928 577 030
Fax: 01928 575 233

KLINGER SOUTHAMPTON

Tel: 02380 611 855
Fax: 02380 610 360

KLINGER ABERDEEN

Tel: 01224 772 962
Fax: 01224 772 953

KLINGER IMMINGHAM

Tel: 01469 575 289
Fax: 08449 676 779

KLINGER MIDDLESBROUGH

Tel: 01642 220 289
Fax: 01642 220 290

KLINGER GRANGEMOUTH

Tel: 01324 472 231
Fax: 01324 482 111