





An exceptional packing combining highpurity carbon, micro-fine wires of Inconel® and a lubricant of selected non-migratory graphite to produce a product for sealing valve glands in high pressure and high temperature applications.

Klinger TopLine packing range introduced to provide users with gland sealing products that meet today's demanding services, offering effective and trouble-free sealing during application. To achieve this goal we have selected the best materials and the best production methods.

GENERAL PROPERTIES


- » K40 has excellent chemical resistance and is unaffected by the majority of acids, alkalis, solvents and greases.
- The incorporation of Inconel wire enhances the packing performance in high pressure steam applications
- » Header and footer rings for graphite ribbon packings like K3222 and K3222W.
- » The additional graphite lubricant improves the sealing effect of K40, producing a dense non-porous matrix. It also improves the frictional properties of the packing, to allow easy operation of any valve stem once installed.

AVAILABILITY

| SIZE (MM) | LENGTH (M) | SIZE (MM) | LENGTH (M) |
|-------------|------------|-------------|------------|
| 3.2 x 3.2 | 8 | 12.5 x 12.5 | 8 |
| 5.0 x 5.0 | 8 | 14.0 x 14.0 | 8 |
| 6.5 x 6.5 | 8 | 16.0 x 16.0 | 8 |
| 8.0 x 8.0 | 8 | 19.0 x 19.0 | 8 |
| 9.5 x 9.5 | 8 | 22.0 x 22.0 | 8 |
| 11.0 x 11.0 | 8 | 25.0 x 25.0 | 8 |



APPLICATION GUIDELINES



Temperature (°C)

- Caution: May be suitable but essential that you refer to Klinger for advice
- Usually Satisfactory, but suggest you refer to Klinger for advice
- Usually Satisfactory to Use Without Reference

NOTE: Chemical compatibility must be considered in all cases.

TYPICAL SPECIFICATIONS

| PROPERTIES | VALUES |
|------------------------|---------|
| Min. Temperature | -100°C |
| Max. Steam Temperature | 650°C |
| Max. Temperature | 430°C |
| Max. Static Pressure | 200 Bar |
| Max. Speed | 5 m/s |
| pH Range | 0-14 |

This packing should not be subjected to maximums of temperature, pressure and speed simultaneously.



9100 Series Aviation, Space FM 602916

ISO 9001 Quality

FM 10571

enquiries@klingeruk.co.uk OHSAS 18001 Occupational Health & Safety Management

OHS 570166

Tel: 01274 688 222

Fax: 01274 688 549

www.klinger.co.uk

14001 Environmenta Management

EMS 570165

KLINGER RUNCORN

Tel: 01928 577 030 Fax: 01928 575 233

KLINGER SOUTHAMPTON Tel: 02380 611 855

Fax: 02380 610 360 KLINGER ABERDEEN

Tel: 01224 772 962 Fax: 01224 772 953

KLINGER IMMINGHAM

Tel: 01469 575 289 Fax: 08449 676 779

KLINGER MIDDLESBROUGH

Tel: 01642 220 289 Fax: 01642 220 290

KLINGER GRANGEMOUTH

Tel: 01324 472 231 Fax: 01324 482 111